

**AMENDMENTS TO THE CLAIMS**

**This listing of claims will replace all prior versions and listings of claims in the application:**

**LISTING OF CLAIMS:**

1. (previously presented): A toner for use in an image-forming apparatus equipped with an oil-less fixing unit comprising a main heating member and a pressing member, the main heating member gets in contact with an unfixed toner surface on a recording medium and fixes the unfixed toner at a nip part of the main heating member and the pressing member, the main heating member and the pressing member define a boundary surface thereof, and the surface takes a configuration protruding toward the pressing member side,

wherein the toner comprises a resin comprising a block polyester and an amorphous polyester, and

the toner has an initial relaxation modulus  $G(t=0.01)$  (Pa) of the toner at 120°C, in relaxation time of 0.01 (sec), of  $G(t=0.01)$  [Pa]  $\geq 1.0 \times 10^5$  [Pa].

2. (original): The toner according to claim 1, wherein the toner contains a release agent in an amount of 3 wt.% or less.

3. (previously presented): A toner for use in an image-forming apparatus equipped with an oil-less fixing unit comprising a main heating member and a pressing member, the main heating member gets in contact with an unfixed toner surface on a recording medium and fixes the unfixed toner at a nip part of the main heating member and the pressing member, the main

heating member and the pressing member define a boundary surface thereof, and the surface takes a configuration protruding toward the side of the main heating member,

wherein the toner comprises a resin comprising a block polyester and an amorphous polyester, and

the toner has a loss tangent  $\tan\delta (= G''/G')$  of the toner, a ratio of loss modulus  $G''$  to storage modulus  $G'$  in dynamic relaxation modulus, of from 1.7 to 5.0 at 120°C.

4. (currently amended): The toner according to claim 34, wherein the toner contains a release agent in an amount of 3 wt.% or less.

5. (previously presented): A toner for use in an image-forming apparatus equipped with an oil-less fixing unit comprising a main heating member and a pressing member, the main heating member gets in contact with an unfixed toner surface on a recording medium and fixes the unfixed toner at a nip part of the main heating member and the pressing member, the main heating member and the pressing member define a boundary surface thereof, and the surface takes a configuration of flat surface,

wherein the toner comprises a resin comprising a block polyester and an amorphous polyester,

the toner has a larger value of loss tangent  $\tan\delta (= G''/G')$  of the toner, the ratio of loss modulus  $G''$  to storage modulus  $G'$  in dynamic relaxation modulus, at 180°C than a value of  $\tan\delta$  at 110°C,

wherein the difference between the values of  $\tan\delta$  at 180°C and 110°C is 1 or more.

6. (original): The toner according to claim 5, wherein the toner contains a release agent in an amount of 3 wt.% or less.

7. (previously presented): An image-forming system comprising:  
an image-forming apparatus; and  
a toner,

wherein said image-forming apparatus is equipped with an oil-less fixing unit comprising a main heating member and a pressing member, the main heating member gets in contact with an unfixed toner surface on a recording medium and fixes the unfixed toner at a nip part of the main heating member and the pressing member, the main heating member and the pressing member define a boundary surface thereof, and the surface takes a configuration protruding toward the pressing member side, and

said toner comprises a resin comprising a block polyester and an amorphous polyester, and has an initial relaxation modulus  $G(t=0.01)$  (Pa) of the toner at 120°C, in relaxation time of 0.01 (sec), of  $G(t=0.01)$  [Pa]  $\geq 1.0 \times 10^5$  [Pa].

8. (previously presented): An image-forming system comprising:  
an image-forming apparatus; and  
a toner,

wherein said image-forming apparatus is equipped with an oil-less fixing unit comprising a main heating member and a pressing member, the main heating member gets in contact with an unfixed toner surface on a recording medium and fixes the unfixed toner at a nip part of the main heating member and the pressing member, the main heating member and the pressing member

define a boundary surface thereof, and the surface takes a configuration protruding toward the side of the main heating member, and

said toner comprises a resin comprising a block polyester and an amorphous polyester, and has a loss tangent  $\tan\delta (= G''/G')$  of the toner, a ratio of loss modulus  $G''$  to storage modulus  $G'$  in dynamic relaxation modulus, of from 1.7 to 5.0 at 120°C.

9. (previously presented): An image-forming system comprising:  
an image-forming apparatus; and  
a toner,

wherein said image-forming apparatus is equipped with an oil-less fixing unit comprising a main heating member and a pressing member, the main heating member gets in contact with an unfixed toner surface on a recording medium and fixes the unfixed toner at a nip part of the main heating member and the pressing member, the main heating member and the pressing member define a boundary surface thereof, and the surface takes a configuration of flat surface, and

said toner comprises a resin comprising a block polyester and an amorphous polyester, and has a larger value of loss tangent  $\tan\delta (= G''/G')$  of the toner, the ratio of loss modulus  $G''$  to storage modulus  $G'$  in dynamic relaxation modulus, at 180°C than a value of  $\tan\delta$  at 110°C,

wherein the difference between the values of  $\tan\delta$  at 180°C and 110°C is 1 or more.